

TEST REPORT

No. : GZIN1501002365MR

Date : Jan 23, 2015

Page: 1 of 3

CUSTOMER NAME: SUZHOU VOLSUN ELECTRONICS TECHNOLOGY CO., LTD.
ADDRESS: BUILDING 5, JINXINGFUMIN INDUSTRIAL PARK, 413 MUDONG
ROAD, MUDU TOWN, SUZHOU CITY, JIANGSU PROVINCE, CHINA

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : EPDM COLD SHRINK TUBE
SGS Ref. No. : SUZPL150100069
Date of Receipt : Jan 16, 2015
Testing Start Date : Jan 16, 2015
Testing End Date : Jan 23, 2015
Test result(s) : For further details, please refer to the following page(s)

Signed for
SGS-CSTC Standards Technical
Services Co., Ltd. GZ Branch Testing
Center

Fiona Lau
Authorized signatory

TEST REPORT

No. : GZIN1501002365MR

Date : Jan 23, 2015


Page: 2 of 3

Summary of Results:

No.	Test Item	Test Method	Result	Conclusion
1	Ozone Aging	ASTM D1149-07(2012) Method B, Procedure B1	No cracking	/

Note: Pass : Meet the requirements;
Fail : Does not meet the requirements;
/ : Not Apply to the judgment.

Original Sample Photo:



TEST REPORT

No. : GZIN1501002365MR

Date : Jan 23, 2015

Page: 3 of 3

Test Item: Ozone Aging

Sample Description: Rubber

Test Method: ASTM D1149-07(2012) Method B, Procedure B1

Test Condition:

Elongation: 20%

Pretreatment temperature: 40°C

Pretreatment period: 24h

Testing temperature: (40±1)°C

Ozone concentration: 50 pphm


Exposure period: 72h

Test result:

Sample	Appearance
1	No cracking

Note: Observation magnification is 7X.

Test Photo:



Reference sample Tested sample

***** End of report*****